



# Fix ALL X-treme Power Express

## Product description

Fix ALL X-treme Power Express is a high quality, neutral, elastic one-component adhesive sealant based on SMX-polymer. Fix ALL X-treme Power Express has an extremely high initial tack of min. 400 kg/m<sup>2</sup>.

## Properties

- Extreme high initial tack of min. 400 kg/m<sup>2</sup>
- Fix ALL X-treme Power Express achieves a hand tight bond in 30 minutes
- Quickly manipulable and very fast strength build-up with thin adhesive layer and on porous substrates.
- Fast curing
- Good workability
- Stays elastic after curing
- Low odour
- Good weather resistance
- Good UV resistance
- Very good adhesion on many materials, even if slightly moist
- Can be painted with water based systems
- Non staining on natural stone



## Applications

- Bonding in building and metal industry.
- Elastic bonding of objects, panels, profiles and other pieces on the most common substrates.
- For bonded facade panels, we refer to the Soudal Panel System.

## Technical data

Base		SMX Hybrid Polymer
Consistency		Stable paste
Curing system		Moisture curing
Skin formation		ca. 4 minutes
Curing speed		ca. 2 mm/24h
Density		ca. 1.48 g/ml
Maximum allowed joint movement		± 20 %
Elasticity modulus	ISO 37	ca. 2.90 N/mm <sup>2</sup>
Elongation at break	ISO 37	ca. 200 %
Maximum tension	ISO 37	ca. 3.60 N/mm <sup>2</sup>
Hardness		ca. 75 ± 5 Shore A
Application temperature		+5°C → +35°C
Temperature resistance		-40°C → +90°C

Footnote: Skinning time and curing speed may vary depending on environmental factors such as temperature, moisture, and type of substrates.





# Fix ALL X-treme Power Express

## Substrates

- **Substrate condition**  
The surface must be rigid, clean, dry, free of dust and grease.
- **Substrate preparation**  
Porous surfaces in water loaded applications should be primed with Primer 150. Prepare non-porous surfaces with a soudal activator or cleaner (see technical data sheet). While producing plastics very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding or sealing. For optimum adhesion the use of Surface Activator is recommended.
- **Substrate types**  
Fix ALL X-treme Power Express has a good adhesion to following substrates: all usual building substrates, lacquered wood, stainless steel, AlMgSi1, electrolytic galvanized steel, AlCuMg1, hot dip galvanized steel, AlMg3, steel ST1403, polystyrene, PVC, polyamide, fiberglass reinforced epoxy. Fix ALL X-treme Power Express has no good adhesion or is not suitable for PE, PP, PTFE (Teflon®), bituminous substrates, copper or copper containing materials such as bronze and brass. Bonding plastics like PMMA (e.g. Plexi® glass), polycarbonate (e.g. Makrolon® or Lexan®) in stress loaded applications can give rise to stress cracking and crazing in these substrates. The use of Fix ALL X-treme Power Express is not recommended in these applications. We recommend a preliminary adhesion and compatibility test on every surface.

## Application method

- **Application method**  
Apply the adhesive by means of a caulking gun in beads or dabs (every 15 cm) on one of the substrates. Always apply adhesive to the edges and corners of the panels. Do not apply the glue in a closed circumference, but interrupted. Bond the substrate and tamp with a rubber hammer. If necessary, support the bonded materials. For bonding on absorbent and porous substrates with thin adhesive layer, the adhesive is already hand tight after ca. 30 minutes and can be loaded after ca. 3 hours. Thicker adhesive layers or non-absorbent substrates extend the curing time. The bond can be fully loaded after 24-48 hours.
- **Cleaning method**  
Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).
- **Finishing method**  
With Finishing Solution before skinning.
- **Repair method**  
Repair with the same material.

## Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label and safety data sheet for more information.  
Keep the area well ventilated during use and curing of the product.  
Dangerous. Respect the precautions for use.

## Packaging/Logistics

Colour: Please consult the product catalogue, the Soudal website or a Soudal representative.  
Packaging: Please consult the product catalogue, the Soudal website or a Soudal representative.  
Shelf life: 15 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C, Once opened the product has only a limited shelf life.

## Standards and certificates

- EC1 Plus label: very low emission
- M1 Emission classification of building materials



# Fix ALL X-treme Power Express

## Environmental clauses

- Leed regulation: Fix ALL X-treme Power Express conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

## Remarks

- Fix ALL X-treme Power Express may be overpainted, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application.
- Fix ALL X-treme Power Express can be applied to a wide variety of substrates. Due to the fact that specific substrates such as plastics, like polycarbonate , etc., may differ from manufacturer to manufacturer, we recommend a preliminary compatibility test.
- Fix ALL X-treme Power Express can not be used as a glazing sealant.
- Not suitable for bonding aquariums.
- Do not use in applications where continuous water immersion is possible.
- Not suitable for sanitary applications.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Fix ALL X-treme Power Express has a good UV resistance but can discolour under extreme conditions or after long UV exposure.
- Discoloration of the product due to chemicals, high temperatures, UV-radiation may occur.
- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discoloration and loss of adhesion.

This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. It is general in nature and does not constitute any liability. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application. In every case it is recommended to carry out preliminary experiments. The manufacturer reserves the right to modify products without prior notice.